



High Dense Zircon Block

Brand: Sunrise

Physical and chemical index

Item	HDZ-68
ZrO ₂ (%)	≥68
SiO ₂ (%)	≤30
Fe ₂ O ₃ (%)	≤0.3
Apparent Porosity (%)	≤8
Bulk Density (g/cm ³)	≥4.15
Cold Crushing Strength (Mpa)	≥200
0.2Mpa Refractoriness Under Load T _{0.6} °C	≥1680
Pyrometric Cone Equivalent S.C. SK	40
Reversible Thermal Expansion 1000°C %	0.5