



High Dense Zircon Block

Brand: Sunrise

Physical and chemical index

Item	HDZ-65
ZrO ₂ (%)	≥65
SiO ₂ (%)	≤33
Fe ₂ O ₃ (%)	≤0.3
Apparent Porosity (%)	≤1
Bulk Density (g/cm ³)	≥4.25
Cold Crushing Strength (Mpa)	≥310
0.2Mpa Refractoriness Under Load T _{0.6} °C	≥1680
Pyrometric Cone Equivalent S.C. SK	40
Reversible Thermal Expansion 1000°C %	0.5