



SILLIMANITE MORTAR SLN-60

Physical and chemical index

Item		SLN-60
Chemical composition	Al ₂ O ₃	≥60
	SiO ₂	≤35
	Fe ₂ O ₃	≤2.0
Refractoriness, °C		≥1700
Bonding MOR , Mpa	110°Cx24h	≥1.96
	After sintering	1400°Cx3h 4.9-6.86
Bonding time, S		45-120 Adjustable
Gain Size,%	<0.076mm	≥50
	>0.5mm	≤1