



High alumina brick LZ-80

Physical and chemical index

Item:		LZ-80
Al ₂ O ₃ %		≥80
Apparent porosity %		≤22
Cold crushing strength Mpa		≥55
Refractoriness °C		≥1790
Refractoriness under loadin 0.2MPa		≥1530
Permanent linear change	1500°C×2h	-0.4~0.1
	1450°C×2h	-