



HIGH ALUMINA BRICK LZ-75

Physical and chemical index

Item:	LZ-75	
Al ₂ O ₃ %	≥75	
Apparent porosity %	≤23	
Cold crushing strength Mpa	≥53.9	
Refractoriness °c	≥1790	
Refractoriness under loadin 0.2MPa	≥1520	
Permanent linear change	1500°c×2h	-0.4~0.1
	1450°c×2h	-