



HIGH ALUMINA BRICK LZ-48

Physical and chemical index

Item:	LZ-48	
Al ₂ O ₃ %	≥48	
Apparent porosity %	≤22	
Cold crushing strength Mpa	≥39.2	
Refractoriness °c	≥1750	
Refractoriness under loadin 0.2MPa	≥1420	
Permanent linear change	1500°c×2h	-
	1450°c×2h	-0.4~0.1