



High Alumina Insulation Brick

Brand: Sunrise

Physical and chemical index

Brand		LG-1.0
Inedx		
Al ₂ O ₃ ,%	≥	48
Fe ₂ O ₃ ,%	≤	2.0
Bulk Density (g/cm ³)	≤	1.0
Cold Crushing Strength Mpa	≥	3.92
Thermal Conductivity (350°C)W/m.K	≤	0.5
Temp reheating shrinkage less than 2.0% °C		1400