



High Alumina Insulation Brick

Brand: Sunrise

Physical and chemical index

Inedx	Brand	LG-0.6
Al ₂ O ₃ ,%	≥	48
Fe ₂ O ₃ ,%	≤	2.0
Bulk Density (g/cm ³)	≤	0.6
Cold Crushing Strength Mpa	≥	1.96
Thermal Conductivity (350°C)W/m.K	≤	0.30
Temp reheating shrinkage less than 2.0% °C		1350