



## High Alumina Insulation Brick

Brand: Sunrise

Physical and chemical index

Brand	LG-0.5
Inedx	
$\text{Al}_2\text{O}_3\% \geq$	48
$\text{Fe}_2\text{O}_3\% \leq$	2.0
Bulk Density ( $\text{g}/\text{cm}^3$ ) $\leq$	0.5
Cold Crushing Strength Mpa $\geq$	1.47
Thermal Conductivity (350°C)W/m.K $\leq$	0.25
Temp reheating shrinkage less than 2.0% °C	1250